



Scotchcal™ Translucent Mirror Graphic Film

7755 SE-520

Scotchcal™ Translucent Mirror Graphic Film with Comply™ adhesive

7755C SE-520

Product Bulletin

Product Description

These special effect films are unique translucent films that reflect the light to produce a glossy chrome appearance in a finished graphic.

This intermediate to long term film can be applied to any plastic sheet. Film SC7755 SE-520 (without Comply) can be thermoformed on a high temperature Copolyester sheet.

It is designed for use on first or second surface signs in an internally illuminated sign box.

For easier converting the films are delivered with a removable protective top film.

Product variants with Comply™ adhesive also have air release channels for fast and easy, bubble-free graphic installations.

Product Line	Illuminated signage	SC7755 SE-520	silver mirror, translucent, high-gloss, permanent adhesive.
		SC7755C SE-520	silver mirror, translucent, high-gloss, permanent adhesive with Comply™.

Product Characteristics

Physical & Application

These are typical values for unprocessed products.
Contact your 3M representative for a custom specification.

Material	PVDF	
Surface finish	high-gloss	
Thickness (film)	50 µm (0.05 mm)	
Adhesive type	solvent acrylic, pressure-sensitive	
	In addition: product variants with Comply™ adhesive have air release channels	
Adhesive appearance	clear	
Liner	double-sided Polyethylene coated paper	
Adhesion	15 N/25 mm	FTM 1: 180° peel, substrate: glass; cond: 24 h 23°C/50%RH
Application method	wet or dry	
	versions with Comply: 7755C SE-520	dry only!
Applied shrinkage	< 0.4 mm	FTM 14
Application temperature	+16°C minimum (air and substrate)	
Service temperature	-29°C to +80°C	
Surface type	flat	
Substrate type	glass, PMMA, PC*, PETG*, ABS	
	PC*, PETG*: Might require drying with heat before use	

Notice! Thermoforming of film SC7755 SE-520 is recommended on high temperature Copolyester only!

Graphic removal Hard to remove from supported substrates.

Important quality notice!

The manufacturing process might produce some visual effects. Slight variations of the grey tone are possible as well as dull milky stripes which might appear over the width of the material. Those type of defects are excluded from any quality complaint.


Storage Shelf life 2 years from the date on the original box
Up to 2 years unprocessed, or
processed within 1 year and apply within 1 year of processing

Storage conditions! +4°C to +40°C, out of sunlight, original container in clean and dry area.

Flammability Flammability standards are different from country to country. Ask your local 3M contact for details, please.

Durability Unprocessed film The following durability data are given for unprocessed film only!
3M Performance Guarantee and MCS™ In addition, 3M provides a guarantee/warranty on a finished applied graphic within the framework of 3M Performance Guarantee and/or 3M MCS™ warranty programs.
Visit www.3mgraphics.com for getting more details about 3M's comprehensive graphic solutions.

Climatic zones Graphic durability is largely determined by the climate and the angle of exposure. Find below a table showing the durability of a product according to the angle of exposure and the geographical location of the application.
Zone 1 Northern Europe, Italy (north of Rome), Russia
Zone 2 Mediterranean area without North Africa, South Africa
Zone 3 Gulf area, Africa

Exposure types Vertical:  The face of the graphic is ±10° from vertical.

Interior: Interior means an application inside a building without direct exposure to elements.

	Zone 1	Zone 2	Zone 3
Vertical outdoor exposure	6 years	5 years	3 years
Interior application	Zone 1	Zone 2	Zone 3
interior	6 years	6 years	6 years

Important notice! Thermoformed film applications do have a lower durability!
Zone 1: 4 years, Zone 2: 3 years, Zone 3: 2 years

Limitations of End Uses

3M specifically does not recommend or warrant the following uses, but please contact us to discuss your needs to recommend other products.

Graphics applied to

- flexible substrates incl. Panaflex™ and Panagraphics™.
- low surface energy substrates or substrates with low surface energy coating.
- other than flat surfaces.
- stainless steel.
- substrates with tendency of outgasing.
- surfaces that are not clean and smooth.

Graphics subjected to

- gasoline vapors or spills.

Important Notice

- 3M Commercial Graphics Division products are not tested against automotive manufacturer specifications!
- Non vertical applications are neither recommended nor warranted.
- Thermoforming with high temperatures is not recommended!
- 3M accepts no liability for glass breakage. See instruction bulletin 5.1 for details.
- Printing on film is not recommended.
- The use of these films in multi-layer constructions is not recommended.
- Do not apply any graphic protection to film surface.

Graphics Manufacturing

Shipping finished graphics

Flat, or rolled film side out on 130 mm (5 inch) or larger core. These methods help to prevent the liner from wrinkling or application tape, if used, from popping off.

Converting Information Electronic Cutting

Based upon cutting evaluations the minimum height for text is 10 mm using upper and lowercase Helvetica Medium. The stroke width should not be lower than 1 mm.

The variable characteristics of electronically controlled cutting equipment require users to verify their specific requirements.

Sharpness of knife blade Dull blades impart a serrated look to the edge of the cut film.

Weight of knife blade The ideal weight slightly scores the liner. Too little weight does not cut completely through the film and the adhesive. Excessive weight cuts the liner and causes the blade to drag, accelerating wear and creating a serrated cut edge on the film.

Weeding The excess film should be weed (removed) as soon after cutting as practical. This is to minimize the effect of possible adhesive flow.

Temperature and relative humidity Temperature and relative humidity are minor considerations, but avoid extreme or rapid fluctuating conditions.

Roll storage Store the film in the same environment as the cutting equipment.

Further information For more details refer to our instruction bulletin 4.1 'Sheeting, Scoring, Film Cutting', please.

[>Instruction Bulletin 4.1'Sheeting, Scoring, Film cutting'<](#)

Converting Information Thermoforming

There are unique health and safety considerations that must be understood prior to vacuum forming faces using translucent films.

Refer to Instruction Bulletin 5.16 'Thermoforming' for special recommendations, limitations and processing requirements when forming with applied films.

[>Instruction Bulletin 5.16 'Thermoforming'<](#)

Elongation limit Forming of applied film on sheets should not exceed 50% elongation.

Forming temperature Film temperatures of more than 165°C may cause the silver appearance to loose gloss and become dull as the film is stretched. To low temperatures cause the film to wrinkle around the returns.

Diffusion Without diffusion light sources will be seen through the translucent silver film when illuminated

Notice! Do not forget to remove the clear protective top film from the mirror surface before drying/forming.

Application

See product bulletin ATR 'application tape recommendations' for information about selection and use of suitable application tapes for this product, please.

[> Product Bulletin Application Tape Recommendations <](#)

Refer to Instruction Bulletin 5.1 'select and prepare substrates for graphic application', for general application information.

[>Instruction Bulletin 5.1 'select and prepare substrates for graphic application'<](#)

Maintenance and Cleaning

Use a cleaner designed for high-quality painted surfaces. The cleaner must be wet, non-abrasive, without strong solvents, and have a pH value between 3 and 11 (neither strongly acidic nor strongly alkaline).

Refer to Instruction Bulletin 6.5 'storage, handling, maintenance and removal of films and sheetings', for general maintenance and cleaning information.

[>Instruction Bulletin 6.5 'Storage, Handling, Maintenance and Removal of Films and Sheetings'<](#)

Remarks This bulletin provides technical information only.

Important notice All questions of warranty and liability relating to this product are governed by the terms and conditions of the sale, subject, where applicable, to the prevailing law.
Before using, the user must determine the suitability of the product for its required or intended use, and the user assumes all risk and liability whatsoever in connection therewith.

Additional Information Visit the web site of your local subsidiary at www.3mgraphics.com for getting more:

- details about 3M™ MCS™ Warranty and 3M™ Performance Guarantee
- additional instruction bulletins
- a complete product overview about materials 3M is offering

3M Europe S.A./N.V.

Hermeslaan 7
1831 Diegem, Belgium

Responsible for this technical bulletin

3M Deutschland GmbH | Display & Graphics Laboratory
Carl-Schurz-Str. 1 | 41453 Neuss, Germany

3M, Controltac, Scotchcal, Comply and MCS are trademarks of 3M Company. All other trademarks are the property of their respective owners.

The use of trademark signs and brand names in this bulletin is based upon US standards. These standards may vary from country to country outside the USA.