

TECHNICAL DATA SHEET

| | |
|----------------------------------------------------------------------------------------------------------|-----------------------------|
| Contra Vision® Performance™ with <u>Grayliner™</u> Replacement Liner WBPRG30C | Page: 1/2 |
| | Revision: D |
| | Date: 07/03/2016 |
| | Replaces: REVISION C |
| | Authors: HBJ |

1. Identification of the product

- 1.1 Commercial product name:** Contra Vision® Performance™
- 1.2 Product Reference number:** WBPRG30C
- 1.3 Supplier:** Contra Vision Supplies Ltd
 Victoria House, 19–21 Ack Lane East
 Bramhall, Stockport
 Cheshire, SK7 2BE United Kingdom
 Tel. +44 161 439 9307
 E-mail: sales@contravision.com
 Web: www.contravision.com

2. Description

Contra Vision® Performance™ WBPRG30C is a White on Black perforated self adhesive vinyl with 30% transparency and a removable, pressure-sensitive adhesive, featuring a Replacement Liner with Grayliner™ technology. This film allows an image to be seen on the outside of a window while allowing viewing through from the inside.

This promotional film features a solid paper liner optimised for solvent, 'eco-solvent' and most latex inkjet printing and screen printing and is not suitable for UV inkjet, or latex inkjet with an optimizer primer.

3. Use

Some countries have laws or regulations requiring minimum light passage that may limit or preclude the use of this product on vehicle windows. The user is responsible for determining and complying with all applicable standards.

Applications that require an optical clear view, such as vehicle window exteriors, should be laminated with a suitable overlaminates. Failure to apply this laminate could result in obstructed or impaired viewing when the product becomes wet.

This product is not recommended for use on glass with coatings such as anti-reflective, self-cleaning and scratch-resistance, which may be damaged during film removal. Not to be applied to fresh paint or ink, polycarbonate, rubber, plastic moldings and certain PVCs. In case of doubt, please test prior to final application.

This product is not recommended for use around a sharp (90°) angle where there is a limited area either side of the angle.

Replacement Liner construction is not recommended for use with UV curing inkjet printers or latex inkjet printers with an optimizer primer. Depending on the brand of ink and density of the print, "bridging" can occur over the perforated holes after removal of the Replacement Liner, in relatively dark areas of a design. This is eliminated with Universal Liner. We therefore recommend Contra Vision® Performance™ featuring a Universal Liner with Grayliner™ technology which is suitable for UV curing inkjet printers and latex inkjet printers with an optimizer primer.

After printing the ink must be thoroughly dry, including in the perforated holes in order to avoid any contamination, particularly during lamination.

Surfaces to which the material will be applied must be thoroughly cleaned from dust, grease or any contamination which could affect the adhesion of the material. Final clean with soap and water. Rinse and dry glass after cleaning. Use a dry application method. The film must not touch the rubber window molding. This minimizes the chance of the graphic absorbing water that may collect in the window edge.

If two graphic panels meet side by side on a window, carefully trim the film so that the panels meet and form a butt seam. Do not overlap the panels.

The graphics should not be washed within 24 hours of application to allow the adhesive to reach its ultimate strength.

TECHNICAL DATA SHEET

| | |
|---------------------------------------------------------------------------------------|-----------------------------|
| Contra Vision® Performance™ with Grayliner™ Replacement Liner WBPRG30C | Page: 2/2 |
| | Revision: D |
| | Date: 07/03/2016 |
| | Replaces: REVISION C |
| | Authors: HBJ |

4. Typical Properties

| PROPERTY | VALUE | NOTES |
|----------------------------------------|--------------------------------------------------------------------------------------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Face film | White on Black laminated polymeric calendered pvc | |
| Thickness of face film | 180µm (7.1 mil) | ±10 µm (±0.4 mil) |
| Hole pattern | 30% transparency 1.50mm (0.059") diameter holes 2.60mm (1.024") between hole centres | Face film and adhesive only |
| Adhesive | Transparent, solvent polyacrylate | |
| Adhesive coating weight | 28g/m ² (0.89 oz/yard ²) | ±3g/m ² (±0.09 oz/yard ²) |
| Liner | Double-sided poly-coated paper Grey tint on silicone coated side | Unperforated Replacement Liner |
| Liner weight | 160g/m ² (4.72 oz/yard ²) | ±5g/m ² (±0.15 oz/yard ²) |
| Minimum application temperature | +5°C (41°F) | Air and substrate |
| Peel adhesion 24 hours | 4N/25mm 36oz/in | Printed film on glass, typical value |
| Peel adhesion 1 month | 4N/25mm 36 oz/in | Printed film on glass, typical value |
| Removability | Minimum 6 months | Clear removability without adhesive residue at 23°C to 25°C (73°F to 77°F) and RH of 50-60% |
| Durability | 3 years | Durability stated is for unprinted and untreated material correctly applied to an inert, vertical substrate subject to Mid-European weathering conditions. Some printing inks and drying or curing regimes may reduce the expected lifetime of the printed graphic. Please consult your ink manufacturer for guidance. Incorrect application methods, inadequate window cleaning and preparation and incompatible window treatments may reduce the expected lifetime of the applied material whether printed or unprinted, overlaminated or unlaminated. Mechanically sustained damage, chemical damage and UV-degradation to printed, unprinted, laminated or unlaminated material may also reduce expected durability. All perforated window films are especially vulnerable to damage along the edges and corners, which may lead to premature failure. Typical application life is up to eighteen months. |
| Shrinkage | x direction 0.05%, y direction 0.32% | |
| Service temperature | -25°C to 65°C (-13°F to 149°F) | |
| Shelf life | 3 years | Under ordinary condition at temperature of 22°C (72°F) and relative humidity of 50-55% |

This document is intended as a source of information, is given without guarantee, and does not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of the product for their specific intended purpose.